

Email: civil.laboratory@norsegroup.co.uk

Gresham Gravel

East Beckham Quarry
Holt Road
Upper Sheringham
NR26 8TN

Our reference No. NNPL2019110731-102

Our Project No 100281

Your Sample Ref B 110731

Your Project or Order No.

Our Quotation No.

Date Report Issued 02 Dec 2019


sales@greshamgravel.co.uk

Page 1 of 1

Particle Size Distribution to BS EN 933-1:2012 by Washing and Sieving

Scheme: Material Analysis Nov '19

Location: Sharp Sand



Sieve Analysis		No Specification	Date received	6-Nov-19
Particle Size mm	Passing %		Date tested	28-Nov-19
500	100		Description Fine, medium and coarse SAND	
300	100			
125	100			
80	100			
63	100			
40	100			
31.5	100			
20	100			
16.0	100			
10.0	100			
8.0	100			
6.30	100			
4.00	96			
2.00	86			
1.00	73			
0.500	49			
0.250	12			
0.125	2			
0.063	0.5			
Uniformity Coefficient*	3		Water content % 3.5	
			Method of analysis Wet sieving	
			Preparation method Riffing	
If a sample Certificate was provided it is available for inspection. The accuracy of information provided by third parties cannot be guaranteed. Water content determined in accordance with BS EN ISO 17892-1 : 2014. Some sieves may have been used that are not included in the R20 series specified in BS EN 933-2.				
* Uniformity coefficient to Spec. For Highway Works, table 6/1 footnote				
Complies with Grading Requirements of SHW Class: 6D 6E&6R 6L HBM 0/20G1 HBM 0/31.5				

This report shall not be reproduced, except in full, without the prior approval of Norfolk Partnership Laboratory

Test Code = 102



Scott Viner (Project Technician)

