

Email: civil.laboratory@norsegroup.co.uk

Gresham Gravel

East Beckham Quarry
Holt Road
Upper Sheringham
NR26 8TN

Our reference No. **NNPL2019110732-102**

Our Project No 100281

Your Sample Ref B 110732

Your Project or Order No.

Our Quotation No.

Date Report Issued 02 Dec 2019


sales@greshamgravel.co.uk

Page 1 of 1

Particle Size Distribution to BS EN 933-1:2012 by Washing and Sieving

Scheme: **Material Analysis Nov '19**

Location: **Mix Sand**



Sieve Analysis	
Particle Size mm	Passing %
500	100
300	100
125	100
80	100
63	100
40	100
31.5	100
20	100
16.0	100
10.0	100
8.0	100
6.30	100
4.00	100
2.00	98
1.00	90
0.500	69
0.250	24
0.125	5
0.063	0.6

No Specification

Date received 6-Nov-19
Date tested 29-Nov-19

Description
Fine, medium and coarse SAND

Water content % 4.5

Method of analysis Wet sieving
Preparation method Riffing

If a sample Certificate was provided it is available for inspection. The accuracy of information provided by third parties cannot be guaranteed. Water content determined in accordance with BS EN ISO 17892-1 : 2014. Some sieves may have been used that are not included in the R20 series specified in BS EN 933-2.

* Uniformity coefficient to Spec. For Highway Works, table 6/1 footnote

Uniformity Coefficient* 3

Complies with Grading Requirements of SHW Class: 6D 6E&6R 6L
HBM 0/20G1 HBM 0/31.5

This report shall not be reproduced, except in full, without the prior approval of Norfolk Partnership Laboratory

Test Code = 102



Scott Viner (Project Technician)

